



PA6G wear

Polyamide

Standard colour: beige

- Over 280mm substitute for POM
- Resistant to mineral oil, HFD-U, HETG=biological base and diluted acids and bases
- Applicable for Backup Rings and Guide Rings

Properties	Value	Unit	DIN Standard
Hardness	85 ± 3	Shore D	DIN 53505
Density	1,15	g/cm ³	DIN 53479
Water absorbtion	6	%/24h	DIN 53495
Fire performance	94V-2		UL 94 Test
Modulus of elasticity in tension	3900-4200	N/mm ²	DIN 53452
Elongation at break	40	%	DIN 53455
Tensile strength at break	88-90	N/mm ²	DIN 53455
Impact strength	No break	kJ/m ²	DIN 53453
Ball indentation hardness	163	N/mm ²	DIN 53456
Heat distortion	0,28	W/mK	DIN 53461
Therm. coefficient of linear exp.	8	1/K.10 ⁻⁵	DIN 53752
Melting point	220	°C	DIN 53736
min. service temperature	-40	°C	
max. service temperature	+110	°C	
Sliding coefficient	0,4	μ	

All above stated data results from random tests which were taken from the ongoing production. All data was established based on standard test-products according to ISO, DIN and ASTM standards and can basically not be carried over to the completed seal.

Our applied technical advice, either oral, written or through tests is given according to our best knowledge. However, this information is to be considered as non-obligatory instruction, also in terms of any protective rights of a third party, and does not exempt you from testing our product in reference to its suitability for the intended process and purpose. Utilisation, application and processing of the products occur entirely outside of our control and are therefore exclusively your responsibility. However, should a case of liability come into question, it will be limited to all damages in the value of the product which we delivered and you used. By all means, we do warrant the impeccable quality of our products in accordance with our general sales and delivery conditions.